

## Description

rbs Asphaltic Compound is a solvent based, cold applied bituminous compound containing a small amount of organic fibre to add strength and stability. It is typically used as a water-repellent and protective coating that is resistant to water almost immediately after application.

Once dry will form an odourless and taint free bitumen film suitable for the protection of above and below ground concrete, brick and blockwork. Suitable for application to a wide range materials including, iron, steel, lead, zinc, aluminium, concrete, stone, wood, felt and brick.

## Advantages

- Used for damp proof membrane within floors and walls.
- Used for fabric protection of sub-structure i.e. foundations, steelwork.
- High bond strength.
- Cold applied, jointless membrane.
- Fast curing, elastic and flexible.

## Directions For Use

- rbs Asphaltic Compound is ready to use and should not be thinned.
- All surfaces should be sound, stable and thoroughly clean and dry.
- Metal surfaces should be wire brushed to remove any rust.
- Where long term protection is required an initial treatment of a rust inhibitive coating should be used.
- Loose or blistered paint should be removed as should tar based paint systems.
- New galvanised surfaces should be roughened with a wire brush or treated with an etch primer.
- Apply first coat to the internal face of the walls at a rate of 1.5m<sup>2</sup> per litre (0.67L/m<sup>2</sup>) by brush allow to dry for 2-4 hours.
- Apply second coat at a rate of 2.5m<sup>2</sup> per litre (0.4L/m<sup>2</sup>) by brush at right angles to the first.
- Care should be taken at positions of detailing such as corners, door jambs and obstructions to ensure continuous protection is achieved.
- Inspect the completed coats prior to any covering work, ensure the membrane is not damaged.

- In the event of damage to the membrane, recoat the area with further liquid at the rates given previously forming 100mm overlaps with existing applications.
- Clean tools and equipment with white spirit – the membrane must always be protected by a layer of concrete, a screed of 50mm minimum thickness, or by brick/blockwork.
- The membrane can also be protected during backfilling by a thickness of EP protection board.

## Packaging

rbs Asphaltic Compound is available in a 25 litre container. IBC's available on request.

## Storage

Keep container closed, Shelf life unopened is at least 12 months. Store indoors away from all sources of ignition, naked flames and hot lights etc.

## Health & Safety

When working with rbs Asphaltic Compound suitable protective clothing, eye/face protection and gloves should be worn. For further health and safety information, please refer to the relevant Safety Data Sheet. VOC Details: EU limit for this product CAT.2(i): 500g/l, this product contains max 270g/ VOC's.

## Important Note

Whilst all reasonable care is taken in compiling technical data on the Company's products, all recommendations or suggestions regarding the use of such products are made without guarantee, since the conditions of use are beyond the control of the Company.

It is the responsibility of the customer to satisfy themselves that each product is fit for the purpose for which they intend to use it. Ensure that the actual conditions of use are suitable, and that in the light of our continual research and development programme, the information relating to each product has not been superseded.

The information given on this sheet is, to the best of our knowledge, true and accurate. No guarantee of the results implied, or any loss or damage arising out of this material, however, are possible as the conditions of application are beyond our control. This is not withstanding any liability arising from the Consumer Protection Act 1987 and the Health & Safety at Work Act. Health and Safety data is available on this product and should be referred to prior to its use

**Resapol**   
**Foundation**

Giving back **with every pack**

For more information on the Resapol Foundation, please visit our website at [www.resapol.com](http://www.resapol.com).

## Resapol Ltd

Unit D4, Moss Industrial Estate, Walter Leigh Way,  
Leigh, Lancashire WN7 3PT

T 0800 083 1942 E [sales@resapol.com](mailto:sales@resapol.com)

[www.resapol.com](http://www.resapol.com)