

rbs Debonding Compound

Description

rbs Debonding Compound is a bituminous solution designed to provide a thick film on dowel bars. Once dry and the concrete cast, movement is achieved between the bar and the surrounding concrete.

Directions For Use

- Apply to dowel bars by brush or by dipping, allowing for a maximum of 10 days between coating and casting of concrete.
- Although satisfactory performance will be obtained at up to 16 days between coating and casting a programmed time limit of 10 days is suggested to allow for un-programmed delays which may occur under site conditions.
- Re-coating will be required if it is beyond 16 days.
- During cold weather thickening of rbs Debonding Compound will occur but do not thin.
- If difficult to apply slightly warm material by the application of indirect heat

Packaging

rbs Debonding Compound is supplied in a 5 litre container.

Storage

Store under dry conditions at ambient temperature and away from direct heat. The shelf life is 12 months when stored as recommended.

Health & Safety

Rubber gloves and goggles should be worn. If in contact with the skin occurs, wash affected areas with proprietary hand cleanser. Eye contamination must be immediately washed with copious amounts ofwater and medical advice sought.

The information given on this sheet is, to the best of our knowledge, true and accurate. No guarantee of the results implied, or any loss or damage arising out of this material, however, are possible as the conditions of application are beyond our control. This is not withstanding any liability arising from the Consumer Protection Act 1987 and the Health & Safety at Work Act. Health and Safety data is available on this product and should be referred to prior to its use

Resapol Ltd

Unit D4, Moss Industrial Estate , Walter Leigh Way, Leigh, Lancashire WN7 3PT T 0800 083 1942 E sales@resapol.com www.resapol.com

Technical Data

Туре	Bitumen
Colour	Black
Solvents	Petroleum spirit
Specific Gravity	0.92
Flash Point	39°C
Average Coverage	1.8-3.6m²/lite. Experience shows that is advisable to calculate on the basis of 1 litre to coat a 35 metre length of 25mm bar or a 43 metre length of 20mm bar.

Important Note

Whilst all reasonable care is taken in compiling technical data on the Company's products, all recommendations or suggestions regarding the use of such products are made without guarantee, since the conditions of use are beyond the control of the Company.

It is the responsibility of the customer to satisfy himself that each product is fit for the purpose for which he intends to use it, that the actual conditions of use are suitable, and that in the light of our continual research and development programme the information relating to each product has not been superseded.



Giving back with every pack

For more information on the Resapol Foundation, please visit our website at www.resapol.com.