

Description

rbs Greencure Sealer is a ultra low odour single pack white polymeric aqueous emulsion designed to impregnate concrete surfaces thus acting as a curing aid, surface sealer, dustproofer and hardener.

Advantages

- Ready mixed curing membrane and surface sealer.
- Ultra low odour.
- Good abrasion resistance.
- One coat spray application.
- Re-coatable with minimum preparation for certain types of coating.
- Extended service life over many commonly used coatings.

Directions for Use

Always stir or shake rbs Greencure Sealer before use.

New concrete – Apply using a fine spray at nominal consumption rate of 5-7m²/litre. Only one coat is required. Care should be taken to ensure full coverage is achieved.

Old concrete – Apply by squeegee, brush or spray at a nominal consumption rate of 6-9m²/litre depending on surface porosity and texture. Never apply rbs Greencure Sealer in external situations where rain or frost is likely to come into contact with uncured material. All equipment should be cleaned with water.

Packaging

rbs Greencure Sealer is available in 5, 20 and 200 Litre containers.

The information given on this sheet is, to the best of our knowledge, true and accurate. No guarantee of the results implied, or any loss or damage arising out of this material, however, are possible as the conditions of application are beyond our control. This is not withstanding any liability arising from the Consumer Protection Act 1987 and the Health & Safety at Work Act. Health and Safety data is available on this product and should be referred to prior to its use

Resapol Ltd

Unit D4, Moss Industrial Estate, Walter Leigh Way,
Leigh, Lancashire WN7 3PT
T 0800 083 1942 E sales@resapol.com
www.resapol.com

Storage

rbs Greencure Sealer should be stored under dry, frost-free conditions away from direct sunlight, under such conditions the shelf life is at least twelve months.

Technical Data

Appearance	White liquid, clear when cured
Specific Gravity @ 15.6°C	1.01 (approx)
Flash Point (PMCC)	>100°C
Curing Efficiency	>75% at 6m ² / litre
Drying Time @ 20°C	Tack free - 1-2 hours Hard dry - 6-10 hours
Compliance	ASTM C-309 Type 1, Class A&B

Important Note

Whilst all reasonable care is taken in compiling technical data on the Company's products, all recommendations or suggestions regarding the use of such products are made without guarantee, since the conditions of use are beyond the control of the Company.

It is the responsibility of the customer to satisfy himself that each product is fit for the purpose for which he intends to use it, that the actual conditions of use are suitable, and that in the light of our continual research and development programme the information relating to each product has not been superseded

Resapol 
Foundation

Giving back with every pack

For more information on the Resapol Foundation, please visit our website at www.resapol.com.