

401 WG EPOXY FLOOR PRIMER

FAST CURING, HIGH PERFORMANCE WATER BASED EPOXY PRIMER/SEALER

DESCRIPTION

401 WG Epoxy Floor Primer is a fast curing, two pack, water dispersible epoxy based primer/sealer/clear coating, especially formulated to meet the technological and ecological requirements of modern building and industrial practice. 401 WG Epoxy Floor Primer should be used in lower temperatures or when rapid overcoating/access is required.

401 WG Epoxy Floor Primer is non-flammable and solvent free, is low odour, and may be applied to dry or damp surfaces. 401 WG Epoxy Floor Primer has excellent adhesion to most building materials, is nontoxic once cured, and consequently is a highly versatile material lending itself to application in many different types of location and circumstances.

ADVANTAGES

- Excellent adhesion to dry or damp surfaces
- Low odour
- Easily applied
- Taint free
- Very good chemical and abrasion resistance
- Economical and versatile

TYPICAL PROPERTIES

Pot life @ 20ºC:	3 hours
Touch dry:	1 hour @ 20ºC
Hard dry:	2 hours @ 20ºC
Adhesion to dry concrete:	4.4MPa
	(concrete failure)
Adhesion to damp concrete:	4.1MPa
	(concrete failure)
Chemical Resistance:	Excellent resistance t dilute acids, dilute alk diasal white spirit, sk

2 hours @ 20°C 4.4MPa (concrete failure) 4.1MPa (concrete failure) Excellent resistance to water, dilute acids, dilute alkalis, petrol, diesel, white spirit, skydrol, etc. Specific advice will be provided by our Technical Department.

COLOUR RANGE

Clear

PACK SIZES

- 5kg composite packs (including base, hardener)
- 15kg composite packs (including base, hardener)

COVERAGE

A 5kg pack is sufficient to prime $25m^2$ of surface. (15kg pack pro rata).

SURFACE PREPARATION

Surfaces should be sound, clean and free from standing water, laitance, oil, grease, and other contaminants. New concrete should be allowed to cure for a minimum of 21 days. Floors should be mechanically abraded,

RECOMMENDED USES

Where a fast overcoating/access is required or when application must be carried out in lower temperatures.
As a primer for our Floor Coatings e.g. <u>304 HD Epoxy Floor</u> Coating, <u>307 Flexible Deck Coat</u>, <u>303 Epoxy Floor Paint</u>, etc.

• As a damp surface primer or sealer for concrete.

• Suitable for use in food factories, abattoirs, dairies, laboratories, warehouses, subways, chemical bunds etc.

scarified, grit blasted or otherwise adequately treated prior to application.

Note: For steel work a coat of <u>404 Epoxy Metal Primer</u> is recommended as a primer instead of 401 WG Epoxy Floor Primer.

Note: Substrates with high moisture content or oil contamination can still be coated in most instances by the inclusion of one of our specialist primers. Please see <u>402 Damp Proof Coating</u> and <u>403 Oil Tolerant Primer</u> for full details.

Northspeed House | Moorview | Holbeck | Leeds | LS11 9NF T: +44 (0)1132 455 450 F: +44(0)1132 452 649 E: sales@rawlinspaints.com W: www.rawlinspaints.com

MIXING

401 WG Epoxy Floor Primer is supplied in pre-weighed containers ready for mixing. Pour the contents of the base container into the curing agent container and thoroughly mix, preferably by mechanical means until a uniform consistency is achieved. A low speed drill with paddle attachment is recommended for mixing operations.

Mixing Ratio

By Volume = 2.2 Base : 1 Curing Agent By Weight = 100 Base : 42.9 Curing Agent

APPLICATION

Apply by brush or roller at a nominal rate of 5m² per Kg.

As a sealer or clear coating, a second coat should be applied after a minimum of 2 hours, and before a maximum of 48 hours.

As a primer, overcoating may be commenced as soon as the initial milky appearance has cleared or within 24 hours at 20°C. Ensure good ventilation during application.

EQUIPMENT CLEANING

Clean equipment with <u>109 Tool Cleaner</u> or a blend of <u>109 Tool Cleaner</u> and water, immediately after use

CURING

401 WG Epoxy Floor primer will be touch dry following 1 hours cure @20°C, and hard dry after 2 hours cure @ 20°C. Full chemical resistance will be attained following 7 days cure @ 20°C.

Good ventilation is essential to allow satisfactory evaporation of water from the film.

STORAGE & SHELF LIFE

Store in dry conditions, out of direct sunlight, at temperatures between 10°C and 25°C.

401 WG Epoxy Floor Primer has a minimum shelf life of 12 months when stored in original, unopened containers in accordance with manufacturer's instructions

LIMITATIONS

- Do not apply to uncured surfaces, or where standing water is present.
- Do not apply to surfaces previously treated with water repellent chemicals
- Do not apply at temperatures below 3°C, or if there is a risk of frost during the initial curing period.
- Do not use 401 WG Epoxy Floor Primer that has exceeded the stated pot life.
- Protect from water splashes during the first 24 hours of cure, as the fresh film is sensitive to water.
- Relative humidity must be below 85% during the early stages of curing.
- Do not apply in badly ventilated areas.

HEALTH & SAFETY

- Avoid contact of the material with skin and eyes.
- Wear gloves and goggles.
- Wash off splashes immediately with soap and water.
- Any eye contamination must be rapidly irrigated with copious amounts of water, and immediate medical attention sought.

Please refer to Material Safety Data Sheet for additional Information.

401 WG Epoxy Floor Primer shall be applied strictly in accordance with the manufacturer's instructions.

For specific advice regarding any aspect of this product, please consult our Technical Department.

The information provided in this Product Data Sheet is intended for general guidance only and is given in good faith based on Rawlins Paints Limited current knowledge and experience. No warranty in respect of fitness for a purpose, or any other liability whatsoever can be inferred from the information contained within this data sheet. Users should determine the suitability of the materials for their particular application and should always refer to the most recent issue of the Product Data Sheet for the product concerned. All materials are supplied in accordance with our standard terms and conditions of sale (available upon request).

The information given in this data sheet is derived from tests and experience with the products and is believed to be reliable. The information is offered without guarantee to enable purchasers to determine for themselves the suitability of the product for their particular application. Any specification or advice given by the Rawlins Paints Limited or its agents is based on the information supplied by the purchaser. Rawlins Paints Limited cannot be held accountable for errors or omissions as a result of that information being incorrect or incomplete. No undertakings can be given against infringement of patents. Some materials are derived from natural sources. As such some variation may occur. Site conditions may also contribute to variation in finish and colour.

Northspeed House | Moorview | Holbeck | Leeds | LS11 9NF T: +44 (0)1132 455 450 F: +44(0)1132 452 649 E: sales@rawlinspaints.com W: www.rawlinspaints.com