

## PRODUCT DATA SHEET

# Sikafloor®-FibreShield

### FIBRE SUPPRESSANT DRY SHAKE FLOOR HARDENER

#### PRODUCT DESCRIPTION

Sikafloor®-FibreShield is a one part, pre-blended, synthetic dry shake hardener for concrete comprising of cement, hard aggregates and compatible admixtures.

#### USES

Sikafloor®-FibreShield may only be used by experienced professionals.

Sikafloor®-FibreShield provides a hard wearing, fibre suppressant dry shake topping for monolithic floors. When sprinkled and trowelled into fresh wet concrete floors, it forms a coloured, wear resistant smooth surface.

Typical uses are in warehouses, distribution centres, factories, manufacturing facilities, aircraft hangars, DIY stores, supermarkets, shopping malls, offices and museums.

#### CHARACTERISTICS / ADVANTAGES

- Appearance of fibres suppressed
- Good impact resistance
- Cost effective, long life floor
- Maintenance free
- Quality assured factory blending
- Dust proof
- Increased resistance to oils and grease

#### APPROVALS / STANDARDS

Cement based screed CT-C80-F8-AR1 according to EN 13813, declaration of performance 01 08 0304 001 0000050, and provided with CE marking.  
Cement based screed Afl according to EN 13813, declaration of performance 01 08 0304 001 0000050, and provided with CE marking.

#### PRODUCT INFORMATION

<b>Chemical Base</b>	Blend of natural aggregates mixed with cement and admixtures.
<b>Packaging</b>	25 kg bags
<b>Appearance / Colour</b>	Powder - Natural (concrete grey)
<b>Shelf Life</b>	9 months
<b>Storage Conditions</b>	Store in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +30 °C.
<b>Bulk Density</b>	~ 2.0 ± 0.1 kg/l

#### TECHNICAL INFORMATION

<b>Abrasion Resistance</b>	Class AR1	(EN 13892-4, BCA)
----------------------------	-----------	-------------------

#### SYSTEM INFORMATION

## System Structure

Substrate	Fresh concrete slab (See Substrate Quality below)
Dry shake	Manual or machine application of Sikafloor®-FibreShield. Levelling of surface by means of power trowel or laser screed. Final smoothing with power trowel.
Curing compound	Sikafloor® ProSeal / ProSeal W / Proseal Pro / Proseal 90

Use products mentioned above as indicated in their respective Product Data Sheets.

## APPLICATION INFORMATION

Consumption	~ 3-5 kg/m <sup>2</sup> . the consumption will depend on application method and the concrete mix (w/c-ratio) This figure does not allow for surface profile and wastage								
Layer Thickness	~2.5–3.0 mm at the recommended coverage of ~5.0 kg/m <sup>2</sup>								
Ambient Air Temperature	+5 °C min. / +30 °C max.								
Relative Air Humidity	30 % min. / 98 % max.								
Substrate Temperature	+5 °C min. / +30 °C max.								
Applied Product Ready for Use	<table><tr><td>Substrate temperature</td><td>Foot traffic</td></tr><tr><td>+10 °C</td><td>~18 hours</td></tr><tr><td>+20 °C</td><td>~12 hours</td></tr><tr><td>+30 °C</td><td>~8 hours</td></tr></table>	Substrate temperature	Foot traffic	+10 °C	~18 hours	+20 °C	~12 hours	+30 °C	~8 hours
Substrate temperature	Foot traffic								
+10 °C	~18 hours								
+20 °C	~12 hours								
+30 °C	~8 hours								

The above values are dependent upon the concrete reaching its design strength for serviceability and will be affected by changing ambient conditions, particularly temperature and relative humidity.

## APPLICATION INSTRUCTIONS

### SUBSTRATE QUALITY

The concrete deliveries must be of consistent quality and comply with local standards. Concrete characteristics are specified by its class determined in the static design and by general recommendations for concrete mix design. W/C- ratio must not be too low as some water is required for hydration of the Sikafloor®-FibreShield. Generally recommended w/c-ratios are between 0.45 and 0.55 and must be consistent while being poured. The compressive strength must be a minimum of 25 N/mm<sup>2</sup>. Use of Sikament® or Sika Viscocrete® super plasticisers is advised to ensure the optimum quality of concrete and where fibres are used, their optimum dispersion within the mix. Air entrained concrete is not a suitable substrate for the application of dry shake hardeners.

### APPLICATION

#### Mechanical Application - Automatic spreader in conjunction with a laser screed

Spread Sikafloor®-FibreShield evenly onto the concrete immediately after screeding at ~5 kg/m<sup>2</sup> in one

application.

#### Manual Application

Dependent on the conditions, remove the surface "bleed" water or allow it to evaporate. Sprinkle Sikafloor®-FibreShield onto the screeded concrete evenly in 2 stages (first stage: 3 kg/m<sup>2</sup>; second stage: 2 kg/m<sup>2</sup>).

Care must be taken to apply the product without creating ripples etc. in the concrete surface.

Compaction: The first application must be worked into the slab followed immediately by application of thesecond stage quantity of Sikafloor®-FibreShield.

Notes:

- Never add water to the surface where the dry shake has been applied.
- Sikafloor®-FibreShield results in the slab surface becoming "stiff" more quickly than usual. Careful trimming must take place along the edges where adjoining slabs are to be poured.
- Final finishing for closing pores and removing undulations can be achieved either by hand or powered trowel.

#### Application Time

Application time for dry shake products is influenced by every variable which affects the placing of concrete, and can therefore vary substantially, depending on the prevailing conditions.

For mechanical application with automatic spreader

and laser screed, the spreading can start almost immediately after concrete has been levelled to allow for the hydration of the dry shake. Compaction with the trowel can start as soon as weight of the power trowels is supported by the concrete.

For manual application, the dry shake must be spread once the concrete can be stepped on, without leaving a print deeper than 3–5 mm.

Periodical checking of the condition and development of the concrete will determine the correct time frame for each stage and sequence of application.

## CURING TREATMENT

Cure and seal Sikafloor®-FibreShield immediately after finishing using a curing compound from the Sikafloor® ProSeal range. (Refer to relevant Product Data Sheet).

Joint: After finishing operations and completing saw cuts, clean off any residual saw lubricant / slurry without delay. Joints can be filled with Sikaflex® PRO-3 or another appropriate Sikaflex® sealant in accordance with the floor design requirements.

## CLEANING OF TOOLS

Clean all tools and application equipment with water immediately after use. Hardened / cured material can only be mechanically removed.

## LIMITATIONS

- Application of Sikafloor®-FibreShield must not be carried out in strong wind or draughts.
- Do not use concrete where some cement has been replaced by fly ash, as this makes the mix sticky and less workable.
- Variations in concrete characteristics such as water content and cement quality may lead to slight colour variations.
- Dry shake hardeners give a finish to concrete with some colour variation across the floor due to the natural variability of the concrete onto which they are applied.
- To ensure optimum colour consistency, it is essential that the floor laying operation is as clean and protected from the environment as possible.
- Colour variation during the drying out period is normal for this system and is to be expected.
- Every effort must be made to ensure an even application of Sikafloor®-FibreShield. Correct timing and trowelling techniques are essential.
- At low relative humidity (below 40 %), efflorescence can appear on the surface.

- At high relative humidity (above 80 %), bleeding, slower curing and hardening can occur and extended finishing operations be required.
- Shrinking joints are to be created within two days.
- Expansion joints are reflected in the surface of the floor.

## VALUE BASE

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### SIKA LIMITED

Watchmead  
Welwyn Garden City  
Hertfordshire, AL7 1BQ  
Tel: 01707 394444  
Web: [www.sika.co.uk](http://www.sika.co.uk)  
Twitter: @SikaLimited

### SIKA IRELAND LIMITED

Ballymun Industrial Estate  
Ballymun  
Dublin 11, Ireland  
Tel: +353 1 862 0709  
Web: [www.sika.ie](http://www.sika.ie)  
Twitter: @SikaIreland



### Product Data Sheet

Sikafloor®-FibreShield  
March 2020, Version 01.02  
020815010030000020

Sikafloor-FibreShield-en-GB-(03-2020)-1-2.pdf